



DATASHEET HANNOART GLOSS



PARAMETER	STANDARD	UNIT																				TOLERANCES
STANDARD QUALITY VALUES																					± 2 SIGMA	
BASIS WEIGHT	ISO 536	g/m ²	90	100	104*	115	118*	130	135	150	160	170	200	220*	225	250	270*	275	300	350	400	± 4 %
BRIGHTNESS (illuminant D65/10°)	ISO 2470	%	98	98	98	98	98	98	98	98	98	98	98	98	98	98	98	98	98	98	98	± 2
GLOSS DIN 75° (MD)	DIN 54502	%	50	53	53	55	55	58	58	58	58	58	58	58	58	58	58	58	58	58	58	± 5
OPACITY	ISO 2471	%	90,5	92,5	93	93,5	94,5	94,5	95	96	96,5	97	98	98,5	98,5	98,5	99	99	99	99,5	99,5	- 1
RELATIVE HUMIDITY (23°C)	TAPPI 502	%	50	50	45	50	45	50	50	50	50	50	50	50	50	50	50	50	50	50	50	± 5
PH VALUE	ISO 6588	-	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	>7	-
SPEC. VOLUME	ISO 534	cm ³ /g	0,71	0,72	0,72	0,71	0,74	0,70	0,70	0,71	0,73	0,73	0,74	0,75	0,73	0,74	0,76	0,75	0,76	0,78	0,80	± 6 %

VALID FROM: 5-FEB-2009
 SUBSTITUTES: 8
 REVISION NO: 9
 ISSUED BY TECHNICAL & DEVELOPMENT MANAGER: H.Haan * US grammages

Printouts are uncontrolled copies.
 Refer to the intranet/internet for the actual version.